



Solar Gard® Safety & Security Window Films

Armorcoat® 14 Mil Clear

Performance Results

4 mm 4/12/4 mm

Visible Light

TR (%)	Transmittance	87	79
--------	---------------	----	----

Solar Energy

SIRR (%)	Selective IR Energy Rejection @280-2500nm	32	-
IRER (%)	IR Energy Rejection @780-2500nm	21	29
UV (%)	Blocked @300 to 380nm	>99	>99
TdW (%)	Fading factor Tdw-ISO @300-700nm	62	56
FR (%)	Fade reduction coefficient	27	24

Physical Properties

Tnom/T(µm)	Thickness Nominal / Overall	350/400
TS- kg/cm ²	Tensile strength	2110
ELONG	Elongation	>100%
PEEL-g/cm	Peel Strength	>985
YIELD-kg/cm ²	Yield Strength (at 5%)	37.8
BREAK-kg/cm	Break Strength	77.0
TEAR-kg	Strength (Graves)	10.5
PUNC-kg	Puncture Strength	105.0

Safety Testing*

EN 12600	Human Impact	1B1
EN 356	Resistance to Manual Attack	P2A/P3A**
ISO 16933, GSA & ASTM	Blast Resistance	YES
Reaction to Fire (SBI EN 13823)		B-s1, d0

*For details on available safety testing and test reports, consult www.solargard.com or inquire with your local authorized dealer/distributor
 ** EN356 IGU P3A 4mm Toughened/12mm/4mm Toughened or EN356 IGU P3A Lamell.



ARMORCOAT 14 MIL CLEAR

SAFE INT